

SYSTEM DATA SHEET

SikaProof® P-1201 System

FULLY BONDED, POST-APPLIED FPO SHEET MEMBRANE WATERPROOFING SYSTEM FOR BASEMENT AND BELOW GROUND STRUCTURES

DESCRIPTION

SikaProof® P-1201 System is a fully bonded composite sheet membrane waterproofing system for reinforced concrete structures. It consists of an embossed flexible polyolefin (FPO) based membrane SikaProof® P-1200 and a 2 component PU adhesive SikaProof® Adhesive-01. SikaProof® P-1201 System is cold-applied and post-applied onto the hardened reinforced concrete structure, without use of heat or open-flames. Suitable for use in hot and tropical climatic conditions.

USES

Damp-proofing, waterproofing and concrete protection for basements and other below ground structures against ground water ingress. Suitable for use on:

- Vertical reinforced concrete walls
- Horizontal reinforced concrete slabs, protrusions, decks and podiums
- Extensions and reconstruction works
- Prefabricated structures

CHARACTERISTICS / ADVANTAGES

- Fully bonded onto the hardened concrete structure
- No lateral water underflow between the reinforced concrete structure and the membrane system
- Highly flexible with crack-bridging abilities
- High watertightness tested according various standards
- Easy to install with fully adhered joints (no welding required)
- Cold applied (no heat or open flames required)
- Temporary resistant to weathering and UV-light during construction
- Resistant to aging
- Resistant to aggressive mediums and gases in natural ground water and soil
- Can be combined with other approved Sika Waterproofing / Joint Sealing Systems

APPROVALS / CERTIFICATES

- Function test, Wissbau, according German standards, test report No. 2016-397

PRODUCT INFORMATION

Packaging	Please refer to the individual Product Data Sheet
Shelf life	Please refer to the individual Product Data Sheet
Storage conditions	Please refer to the individual Product Data Sheet

SYSTEMS

System Structure	SikaProof® P-1201 System	
	Waterproofing Membrane	SikaProof® P-1200
	Adhesive	SikaProof® Adhesive-01
See current Method Statement of the SikaProof® P-1201 System for compatible accessories and complementary products used to create the relevant details and connections.		

TECHNICAL INFORMATION

Resistance to Root Penetration	Pass	(CEN/TS 14416)
Tensile Adhesion Strength	≥ 1.5 N/mm ²	(EN 1542)
Adhesion in Peel	≥ 80 N/50 mm, to hardened structural concrete	(EN 1372)
Joint Peel Resistance	≥ 50 N/50 mm	(EN 12316-2)
Reaction to Fire	Class E	(EN 13501-1)
Accelerated Ageing in Alkaline Environment	Pass	(EN 1847) (28 d / +23 °C) (EN 1928, Method B) (24 h / 60 kPa)
Resistance to lateral water migration	Pass, up to 7 bar (area)	(ASTM D 5385 modified)
Service Temperature	-10 °C min. / +35 °C max.	

APPLICATION INFORMATION

Ambient Air Temperature	+5 °C min. / +50 °C max.	
Consumption	~1.50 kg/m ² /mm SikaProof® Adhesive-01 This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level or wastage etc..	
Substrate Temperature	Surface to be bonded: Minimum +5 °C Apply appropriate measures if below	
Substrate Moisture Content	Dry, ≤ 4 % moisture content or contact Sika Technical Department, no rising moisture	
Pot Life	Temperature	Pot Life
	+20 °C	~30 min
	+30 °C	~15 min
Open Time	Temperature	Open Time
	+20 °C	~100 min
	+30 °C	~50 min

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Reinforced concrete structure must be:

- Hardened and of sufficient compressive strength, minimum 25 N/mm²
- With a minimum pull-off strength of 1.5 N/mm²
- Dry, sound, clean and free of any contaminations (example: dust, oil, grease, cement laitance, release agent, etc.)
- Free from surface defects (example: blowholes, voids, honeycombing, cracks, protrusions, etc.)

SUBSTRATE PREPARATION

The concrete or other suitable cementitious substrate must meet the defined substrate quality. If the substrate does not fulfil the requirements, the surface must be pre-treated prior to the application, in order to prevent any subsequent damage to the membrane sheets.

For more detailed information and guidance please refer to the current Method Statement for the

SikaProof® P-1201 System.

APPLICATION METHOD / TOOLS

The installation method of SikaProof® P-1201 System is state of the art for adhered membrane systems, by simple and easy bonding of the membrane sheets onto a previously applied adhesive bed. The following working steps are to be complied with:

- Substrate preparation and cleaning, to fulfil requirements on substrate quality.
- Mix the 2-C SikaProof® Adhesive-01 according to the Product Data Sheet.
- Apply the adhesive with a notched trowel onto the substrate full surface (no primer required).
- Prepare and apply the SikaProof® P-1200 membrane accordingly.
- Roll in and press the membrane properly into the still fresh adhesive bed.
- Ensure a minimum adhesive layer thickness of 1 mm is maintained after pressing.
- Overlap and adhere the membrane sheets, with a minimum bonded overlap of 90 mm.
- Treat all details and connections according to the

Method Statement.

For more detailed information and guidance please refer to the current Method Statement for the SikaProof® P-1201 system.

IMPORTANT CONSIDERATIONS

SikaProof® P-1201 System must only be installed by Sika trained and approved contractors.

- The SikaProof® P-1201 System Method Statement, with its technical guidelines and information, must be complied with.
- Do not install SikaProof® P-1201 System during continuous or prolonged rain, snowfall or sand storm.
- The substrate quality and condition must be fulfilled or appropriate treatment or measures must be applied.
- An adequate concrete quality (mix design and workmanship) is required to achieve optimum full bond of the SikaProof® P-1201 System membrane system to the hardened structural concrete.
- Additional Sika® Joint Sealing Solutions (minimum SikaSwel®) must be used for connections, around penetrations and in construction and expansion joints depending on the project requirements.
- Protect the membrane system immediately after completion of installation works to prevent any damages.
- SikaProof® P-1201 System is not resistant to permanent UV exposure and weathering. It must always be protected against UV exposure as soon as possible, at the latest 3 months (90 days) after installation. For further information please refer to the current Method Statement of SikaProof® P-1201 System.
- SikaProof® P-1201 System must not be installed on structures permanently exposed to UV light and weathering.
- SikaProof® P-1201 System is not designed for use on structures with direct impact of traffic.

For more detailed information and guidance please refer to the current Method Statement for the SikaProof® P-1201 System.

Recommended standard use:

Sika recommends using the SikaProof® P-1201 System for damp proofing or waterproofing of below ground constructions up to a certain demand. Refer to section "Project Design" of the current Method Statement SikaProof® P-1201 System for selecting the most suitable type of SikaProof® membrane system.

Contact Sika Technical Department for additional information and assistance on the selection and specification of the appropriate solution for the specific project.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF
 Bahrain / Qatar / Kuwait
 Tel: +973 177 38188
 sika.gulf@bh.sika.com
 gcc.sika.com

SIKA SOUTHERN GULF
 UAE / Oman / SIC
 Tel: +971 4 439 8200
 info@ae.sika.com
 gcc.sika.com

SIKA SAUDI ARABIA
 Riyadh / Jeddah / Damman
 Tel: +966 11 217 6532
 info@sa.sika.com
 gcc.sika.com

