

PRODUCT DATA SHEET

Sikagard[®]-740 W

SILANE BASED REACTIVE WATER REPELLENT IMPREGNATION

DESCRIPTION

Sikagard[®]-740 W is a one-component low viscosity, reactive impregnation for concrete and cementitious substrates based on concentrated Silane emulsion. Sikagard[®]-740 W complies with the requirements of EN 1504-2 for hydrophobic Impregnation (penetration depth class I & resistance to freeze and thaw salt stresses) Suitable to use in hot and tropical climatic conditions.

USES

Sikagard[®]-740 W is used as water-repellent impregnation (hydrophobic treatment) for absorbent substrates such as concrete in civil engineering or building concrete structures in both vertical and horizontal traffic area:

- Suitable for protection against ingress (Principle 1, method 1.1 of EN 1504-9)
- Suitable for moisture control (Principle 2, method 2.1 of EN 1504-9)
- Suitable for increasing the resistivity (Principle 8, method 8.1 of EN 1504-9)

CHARACTERISTICS / ADVANTAGES

- Good penetration
- Economic and easy to use
- Reduces capillary water absorption, protection against driving rain and splashing on vertical areas
- Reduction of absorption of aggressive or deleterious agents dissolved in water (i.e. chlorides)
- No change in water vapour permeability
- Increases the resistance of concrete to freeze and thaw cycles and de-icing salts
- Water based emulsion, Low VOC
- Resistant to sea water
- Ready to use

APPROVALS / CERTIFICATES

- Conformity to the requirements of the EN 1504-2 class I – MPL, Sika Tüffenwies dated July 2009
- CTL (US) report, April 2009: Scaling resistance (ASTM C 627 / C 672M-03), Rapid Chloride permeability (ASTM C 1202-08), NCHRP Report 244 Series II & IV, AASHTO T 259 & T 260 Chloride penetration.
- AMEC (Canada), January 2010, Compliance to ALBERTA Infrastructure and transportation specifications
- Hydrophobic impregnation according to EN 1504-2, DoP 02 03 03 01 002 0 000048 1105; certified by Factory Production Control Body: 0921; certificate 0921-CPD-2050 and provided with the CE-mark

PRODUCT INFORMATION

Composition	Alkoxysilane
Active content	~40%
Packaging	20 l pail and 200 l drum
Shelf life	12 months from date of production if stored in unopened, undamaged and original sealed packaging.
Storage conditions	Store in dry and cool conditions. Protect from moisture and frost.

Appearance and colour	Milky water like liquid emulsion.	
Density	~0.950 kg/l (at +25 °C)	
Volatile organic compound (VOC) content	< 350 g/lt	(ASTM D 5095 91 / EPA Method 24)

TECHNICAL INFORMATION

Penetration depth	< 10 mm	Class I	(EN 1504-2)
	*Test performed on concrete with a W/C = 0.70		
Water absorption	< 7.5%		(EN 13580)
Drying rate coefficient	Class I:	>30%	(EN 13579)
Resistance to alkalinity	< 10%		(EN 13580)
Freeze thaw de-icing salt resistance	Complies		(EN 13581)

SYSTEM INFORMATION

System structure	2–3 coats applied "wet on wet"
-------------------------	--------------------------------

APPLICATION INFORMATION

Consumption	Dependent on absorbency of the substrate as well as the required penetration depth: ~ 100 to 150 g/m ² per coat
Ambient air temperature	+5 °C min. / +35 °C max.
Substrate temperature	+5 °C min. / +35 °C max.
Substrate moisture content	<5-6% when measured with Tramex method
Waiting time to overcoating	Can be overcoated with water and solvent based polymer paint - contact the proposed paint manufacturer for recommendations. Sikagard®-740 W can be used as a water repellent primer under many Sikagard® protective coatings. Penetration of water is thus prevented at possible weak spots or in the event of damage to the top coat and the risk of consequential damages such as paint flaking can be reduced. Waiting time: minimum 5 hours, maximum 1 week.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Best results are achieved when Sikagard®-740 W is applied on 28 days old concrete – however, due to its high alkali resistance; it is still possible to apply it at an early age – lower penetration might then be expected.
- Areas such as window frames which still need to be painted must be securely covered to avoid contact with Sikagard®-740 W.
- Areas not to be impregnated such as window panes need to be protected from being accidentally contaminated with Sikagard®-740 W.
- Sikagard®-740 W can damage some coatings and bituminous products.
- In rare cases, Sikagard®-740 W might lead to light

darkening of concrete. Final appearance greatly depends from type of concrete substrate, always apply sample area first.

- Due to incoherent composition of concrete substrate, it is recommended to apply sample size not less than 10 m².
- Cannot be overcoated with limewash or cement paint.
- Apply Sikagard®-740 W onto a sample area to confirm consumption rates versus penetration depth.
- Refer to the latest Method Statement for detailed information regarding surface preparation, application method, etc.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Free of dust, dirt, oil, efflorescence and existing paint coatings.

Cracks in concrete more than 300 µm must be repaired first prior to carry out the hydrophobic treatment.

Cleaning is best done with suitable detergents or by light blastcleaning, steam cleaning etc.

Best results are obtained on dry, very absorbent substrates. The substrate must look dry with no damp patches.

MIXING

Sikagard®-740 W is supplied ready for use and must not be diluted.

APPLICATION

Sikagard®-740 W is applied using a low-pressure spray, airless spray, brush or roller, in a single pass from bottom up taking care not to let the product run. Apply subsequent pass "wet on wet" until the required consumption is achieved.

On horizontal surface, use flooding technique but avoid excessive ponding on the surface.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Kuwait
Tel: +973 177 38188
info@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

Sika Saudi Arabia

Riyadh / Jeddah / Dammam
Tel. +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (C),
Sika Saudi Arabia Limited,
Sika International Chemicals LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (C),
Sika Saudi Arabia Limited,
Sika International Chemicals LLC,
ISO 45001: Sika UAE LLC,
Sika Gulf B.S.C. (C),
Sika International Chemicals LLC.

All products are supplied under
a management system certified
to conform to the requirements
of the quality, environmental
and occupational health &
safety standards ISO 9001,
ISO 14001 and ISO 45001.

Sikagard-740W-en-AE-(09-2022)-1-2.pdf

Product Data Sheet

Sikagard®-740 W

September 2022, Version 01.02
020303010020000043

