

PRODUCT DATA SHEET

SikaLatex[®]-10 GRC

WATER BASED ACRYLIC COPOLYMER FOR GRC, GFRC & CEMENT MORTARS.

DESCRIPTION

SikaLatex[®]-10 GRC is an acrylic copolymer emulsion for adding to GRC, GFRC & cement mortars, to enhance adhesion, water resistance and other physical properties of mortars. Suitable for use in hot and tropical climatic conditions.

USES

SikaLatex[®]-10 GRC is used as bonding agent and site mix mortar admixture for the following applications:

- For the application of thin layer patching mortars
- Renders
- Screeds
- GRC/GFRC elements
- For Concrete repair mortars
- Tile adhesives
- Masonry mortars
- Bonding slurry for fresh to old concrete

FEATURES

- Improved workability of the mix at low water/cement ratios, further enhancing the properties of the cured cement matrix
- Easy spraying for vertical surfaces without sagging effect
- Suitable for indoor and out door applications
- Dense and uniform surface appearance on the cured mortar.
- Reduction in moisture absorption and vapor permeability
- Reduce cracks

PRODUCT INFORMATION

Composition	Acrylic copolymer emulsion
Packaging	210 L drum, 1000 L flowbin or bulk supply in tanker
Colour	White liquid
Shelf life	12 months from date of production if stored properly
Storage conditions	Store in undamaged and unopened, original sealed packaging, in cool and dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight and frost.
Density	~1.040 kg/l (+25 °C)
pH-Value	8.0 - 10
Solid content	50%
Viscosity	50-250 cps (16°C)
Total chloride ion content	Nil

APPLICATION INFORMATION

Mixing ratio	Mortars	Cement	Sand	SikaLatex®-10 GRC	Water
Premix		100	85	8-12	20-30
Spary		100	100	10-16	20-30

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Never use pure SikaLatex®-10 GRC or SikaLatex®-10 GRC-water mix directly onto the substrate as bonding bridge, always add cement and sand to the mix.
- The standard rules of good practice for production and placing of bonding bridge, repair and adhesive mortars must be observed when using SikaLatex®-10 GRC. Refer to relevant standards.
- Fresh applied mortar must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika®Antisol® as curing agent or apply curing by polyethylene sheet and wet hessian.
- Higher dosages can be used depending on the mix design, raw materials, climatic conditions and mortar requirements.
- Trial mixes must be performed to evaluate suitability and performance of the final product and to establish the exact dosage rate required.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Substrate preparation to be done based on the type of application (bonding slurry, render, concrete etc). Please refer to relevant standards and guidelines.

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete or plaster surfaces should be clean, sound, rough and free from oil, grease cement laitance, loosely adhering particles or any other bond inhibiting substances. The surface should be in a saturated surface dry (SSD) condition.

MIXING

Bonding Slurry:

SikaLatex®-10 GRC : Water = 1 : 1 Mix together with fresh cement and fine sand to a homogeneous slurry consistency applicable by brush. The resultant bonding slurry should be brushed well onto the prepared surface.

Mortars and Renders:

Mixing can be done in any suitable concrete mixer such as a pan mixer. First add the cement and aggregates into the mixer and mix to a uniform consistency. Then add the required quantity of diluted SikaLatex®-10 GRC and mix slowly for at least 2 minutes. Apply by steel trowel and finish with a wooden float.

Glass Fibre Reinforced Concrete:

Recommended dosage for GFRC mix is 8 -10 % by weight of cement. Always add it after adding the water and plasticizer inside the mixer while its running. To achieve better results and greater strengths.

DISPENSING

SikaLatex®-10 GRC is generally added to the clean mixing water within the range of 1 : 1 to 1 : 2. For all applications, apart from sprayed on renders, bonding slurry should be applied. The subsequent mortar application must be carried out whilst the bonding coat is still wet.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 9200 22167

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikaLatex-10GRC-en-AE-(12-2024)-1-1.pdf

Product Data Sheet

SikaLatex®-10 GRC

December 2024, Version 01.01

020301010010000387