

PRODUCT DATA SHEET

Sikasil[®]-117 BH

Acetoxy silicone sealant for sanitary applications

DESCRIPTION

Sikasil[®]-117 BH is a 1-component, solvent-free sealant with resistance to fungus. Suitable for use in hot and tropical climatic conditions.

USES

Sikasil[®]-117 BH is designed for sanitary or other sealing applications in wet rooms where mildew resistance is required. Sikasil[®]-117 BH is designed to seal glass, glazed surfaces, ceramic and porcelain and coated metal substrates.

CHARACTERISTICS / ADVANTAGES

- Low shrinkage
- Mildew and fungus resistant
- Good UV and weathering resistance

SUSTAINABILITY

- Sikasil[®]-117 BH conforms to LEED[®] v3 IEQ 4.1
- VOC content <50 g/l (US EPA method 24)

PRODUCT INFORMATION

Composition	Acetoxy silicone
Packaging	280 ml cartridges, 12 cartridges per box
Shelf life	Sikasil [®] -117 BH has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikasil [®] -117 BH shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Colour	White and transparent
Density	~0.96 kg/l (ISO 1183-1)
Volatile organic compound (VOC) content	<50 g/l (US EPA method 24)

TECHNICAL INFORMATION

Shore A hardness	~20 (28 d / 23 °C / 50 % r.h.)	(ASTM D-661)
Tensile strain at break	~390 %	(ASTM D-412)
Service temperature	-40 °C min. / +180 °C max.	

APPLICATION INFORMATION

Sag flow	Non sag	(ASTM C-639)
Ambient air temperature	+5 °C min. / +45 °C max.	
Substrate temperature	+5 °C min. / +45 °C max.	
Curing rate	~3 mm/24 h (23 °C / 50 % r.h.)	(CQP 049-2)
Skimming time	~15 min (23 °C / 50 % r.h.) (CQP	(CQP 019-1)
Tack free time	~25 min (23 °C / 50 % r.h.)	(CQP 019-1))

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Do not use Sikasil®-117 BH on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use in totally confined spaces, Sikasil®-117 BH requires atmospheric moisture to cure.
- Sikasil®-117 BH is not recommended for porous substrates, such as concrete, stone, marble and granite. Bleeding can occur when Sikasil®-117 BH is used on these substrates.
- Sikasil®-117 BH is not recommended for use on submerged joints, joints where physical abuse or abrasion are likely to occur, structural glazing or insulated glazing, and food contact applications.
- Do not use Sikasil®-117 BH for medical or pharmaceutical uses.
- Acetic acid released during the curing of Sikasil®-117 BH can cause the corrosion of mirror silver and sensitive metals such as copper, brass and lead.
- Do not use Sikasil®-117 BH on alkaline surfaces such as concrete, plaster and brick.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sikasil®-117 BH adheres without primers and/or activators. However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pretreatment procedures shall be followed: Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of >15 minutes (<2 hours). Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of >30 minutes (<4 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of >30 minutes (<4 hours). Glass shall be cleaned with isopropyl alcohol before application.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly. For more detailed advice and instructions please contact our Technical Department.

APPLICATION METHOD / TOOLS

Sikasil®-117 BH is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sikasil®-117 BH into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikasil®-117 BH sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Do not use tooling products containing solvents.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Kuwait
Tel: +973 177 38188
info@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

Sika Saudi Arabia

Riyadh / Jeddah / Dammam
Tel. +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001, 14001, 45001 –
Lloyd's Register
Sika S.A.C. LLC
Sika International Chemicals LLC
ISO 9001, 14001, 45001 – SGS
Sika Gulf S.S.C. O.
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited

All products are supplied under
a management system certified
to conform to the requirements
of the quality, environmental
and occupational health &
safety standards ISO 9001, ISO
14001 and ISO 45001.



Sikasil-117BH-en-AE-(05-2023)-1-1.pdf

Product Data Sheet

Sikasil®-117 BH

May 2023, Version 01.01
02051403000000251