

PRODUCT DATA SHEET

Sarnafil® TG 76-12 Felt

POLYMERIC MEMBRANE FOR ADHERED ROOF WATERPROOFING



DESCRIPTION

Sarnafil® TG 76-12 Felt (thickness 1.2 mm) is a multi-layer, synthetic roof waterproofing sheet based on premium-quality flexible polyolefins (FPO), containing stabilizers, with inlay of glass non-woven and Polyester fleece backing according to EN 13956.

Sarnafil® TG 76-12 Felt is a hot air weldable, UV-resistant roof membrane. Sarnafil® TG 76-12 Felt is produced with an inlay of glass non-woven for dimensional stability.

Suitable for hot and tropical climatic conditions.

USES

Roof waterproofing membrane for fully bonded exposed roofs with Sarnacol® 2142 S

Approved Substrates:

- Slated/mineralized bitumen sheets; new and aged
- OSB, plywood, fibre cement boards
- Mineral fibre boards (Example: Bondrock MV)
- PUR/PIR insulation boards, (Example: Sarnatherm PIR GT, Kingspan TR 27)
- Concrete, lightweight concrete

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Various colours available
- Resistant to permanent UV irradiation
- High dimensional stability due to glass fleece inlay
- Resistant to all common environmental influences
- Resistant to micro-organisms
- Compatible to old bitumen
- Hot air welding without use of open flames
- Recyclable

APPROVALS / CERTIFICATES

- Sarnafil® TG 76-12 Felt is designed and manufactured to meet the most international recognised standards.
- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-3914 and provided with the CE marking.
- Reaction to fire according to EN 13501-1.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: BROOF(t1).
- Official Quality Approvals and Agreement Certificates.
- Monitoring and assessment by approved laboratories.

PRODUCT INFORMATION

Packaging	Sarnafil® TG 76-12 Felt standard rolls are wrapped individually in a blue PE-foil.	
	Packing unit	See price list
	Roll length	20.00 m
	Roll width	2.00 m
	Roll weight	60.00 kg
Appearance / Colour	Surface	Matt
	Colours	
	Top surface	Beige Grey (nearest RAL 7040)
	Bottom surface	Black
Shelf life	5 years from date of production in unopened, undamaged and original packaging.	
Storage conditions	Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage.	
Product Declaration	EN 13956	
Visible Defects	Pass	(EN 1850-2)
Length	20 m (-0 % / +5 %)	(EN 1848-2)
Width	2 m (-0.5 % / +1 %)	(EN 1848-2)
Effective Thickness	1.2 mm (-5 % / +10 %)	(EN 1849-2)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per unit area	1.5 kg/m ² (-5 % / +10 %)	(EN 1849-2)

TECHNICAL INFORMATION

Resistance to Impact	Hard substrate	≥ 600 mm	(EN 12691)
	Soft substrate	≥ 1250 mm	
Hail Resistance	Rigid substrate	≥ 18 m/s	(EN 13583)
	Flexible substrate	≥ 26 m/s	
Resistance to Static Load	Soft substrate	≥ 20 kg	(EN 12730)
	Rigid substrate	≥ 20 kg	
Tensile Strength	Longitudinal (md) ¹⁾	≥ 800 N/50 mm	(EN 12311-2)
	Transversal (cmd) ²⁾	≥ 600 N/50 mm	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Elongation	Longitudinal (md) ¹⁾	≥ 50 %	(EN 12311-2)
	Transversal (cmd) ²⁾	≥ 50 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Dimensional Stability	Longitudinal (md) ¹⁾	≤ 0.2 %	(EN 1107-2)
	Transversal (cmd) ²⁾	≤ 0.1 %	
	¹⁾ md = machine direction ²⁾ cmd = cross machine direction		
Joint Peel Resistance	≥ 300 N/50 mm		(EN 12316-2)

Joint Shear Resistance	≥ 500 N/50 mm	(EN 12317-2)
Foldability at Low Temperature	≤ -30 °C	(EN 495-5)
External Fire Performance	BROOF(t1) < 20°	(EN 1187) (EN 13501-5)
Reaction to Fire	Class E	(EN ISO 11925-2, classification to EN 13501-1)
Effect of Liquid Chemicals, Including Water	On request	(EN 1847)
Exposure to Bitumen	Pass ³⁾ <small>³⁾ Sarnafil® T is compatible to old bitumen</small>	(EN 1548)
Resistance to UV Exposure	Pass (> 5 000 h / grade 0)	(EN 1297)
Water Vapour Transmission	μ = 150 000	(EN 1931)
Watertightness	Pass	(EN 1928)

SYSTEMS

System Structure	Wide range of accessories is available e.g. prefabricated parts, roof drains, scuppers and walkway pads. The following accessories shall be used: <ul style="list-style-type: none"> ▪ Sarnafil® T 66-15 D Sheet for detailing ▪ Sarnafil® T Metal Sheet ▪ Sarnabar ▪ Sarnafil® T Prep ▪ Sarnacol® T-660 ▪ Sarnacol® 2142S ▪ Sarnafil® T Clean
Compatibility	Sarnafil® TG 76-12 Felt may be installed on all thermal insulations and levelling layers suitable for roofing. No additional separation layer is required. Sarnafil® TG 76-12 Felt is suitable for installation directly on top of existing, carefully cleaned, level bituminous roofing, example re-roofing over old flat roofs. Colour changes in membrane surface may occur in case of direct contact with bitumen. Sarnacol®-2142 S single-component PUR adhesive is designed for adhering feltbacked Sarnafil® TG 76-12 Felt to standard insulations and substrates. Adhering Sarnafil® TG 76-12 Felt by means of Sarnacol®-2142 S is particularly suitable for re-roofing over old bitumen waterproofing. (Not suitable for re-roofing over synthetic, rubber or ECB roofing).

APPLICATION INFORMATION

Ambient Air Temperature	-20 °C min. / +60 °C max.
Substrate Temperature	-30 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc.
The supporting layer must be compatible to the membrane and free of oil and grease. Cut open any blisters in the old waterproofing and repair.
The safety of the existing roof assembly in terms of wind uplift must be ensured. Any insufficiently secured sections or components (example chippings, slating etc.) must be removed to provide a smooth surface.

The curing of Sarnacol®-2142 S requires moisture. The base layer may therefore be slightly moist (no puddles). If the relative humidity is below 35 % moisten the adhesive after it has been applied.

APPLICATION

Installation works to be carried out only by Sika instructed contractors for roofing.
Installation of some ancillary products, example contact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.
Special measures may be compulsory for installation

below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

APPLICATION METHOD / TOOLS

Installation procedure:

According to the valid installation instructions for systems with Sarnafil® TG 76 Felt-types for fully adhered roofs.

Adhering:

- Use Sarnacol®-2142 S only at temperatures above +5 °C
- Use only on slopes less than 10°
- Lay out and align Sarnafil® TG 76-12 Felt with the felt-free edge along upstands.
- From the end of the run fold back Sarnafil® TG 76-12 Felt to approximately halfway.
- Using a roller (pile length approximately 15 mm) apply Sarnacol® 2142 S evenly over the surface exposed by the folded back Sarnafil® sheet.
- Very absorbent surfaces, example mineral fibre, require two coats of adhesive. The first coat of approx 300 g/m² must be completely dry before applying the second.
- Roll the folded back Sarnafil® TG 76-12 Felt sheet immediately into the wet adhesive.
- Press down the Sarnafil® TG 76-12 Felt with a weighted roller (50 kg).
- Fold back the other half of the Sarnafil® TG 76-12 Felt membrane.
- According to site conditions (roof geometry) adjoin the next Sarnafil® sheet at the end of the adhered membrane to form a butt joint or lay the following rolls alongside with overlapped joints.
- Peeling protection must be provided at all upstands and roof penetrations, as work proceeds. The roof built up must be mechanically secured by a peel stop using Sarnabar.

Welding:

- The adhered Sarnafil® TG 76-12 Felt may only be welded together after the adhesive bond is sufficiently strong.
- Butt joints should be covered with a Sarnafil® TG 66-15 cover strip welded on either side.

Welding Method:

Before welding the seams are prepared with Sarnafil® T Prep. Overlap seams are welded by electric hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.

Recommended type of equipment:

- Leister Triac PID for manual welding
- Sarnamatic 661^{plus} / 681 for automatic welding

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air should be minimum 20 mm.

The seams must be mechanically tested with screw

driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

IMPORTANT CONSIDERATIONS

Geographical / Climate

Permanent ambient temperature during use is limited to +50 °C.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet
Sarnafil® TG 76-12 Felt
August 2017, Version 03.01
020910052000121001

SarnafilTG76-12Felt-en-AE-(08-2017)-3-1.pdf

